

February 2001

SET based experiments for HTSC materials II

Sher Alam¹, M. O. Rahman², H. Oyanagi², and T. Yanagisawa¹

¹*Photonics, AIST, Tsukuba, Ibaraki 305, Japan*

²*GUAS & Photon Factory, KEK, Tsukuba, Ibaraki 305, Japan*

³*Quantum Nanoelectronics, AIST, Tsukuba, Ibaraki 305, Japan*

Abstract

The cuprates seem to exhibit statistics, dimensionality and phase transitions in novel ways. The nature of excitations [i.e. quasiparticle or collective], spin-charge separation, stripes [static and dynamics], inhomogeneities, psuedogap, effect of impurity dopings [e.g. Zn, Ni] and any other phenomenon in these materials must be consistently understood. In this note we further discuss our original suggestion of using Single Electron Tunneling Transistor [SET] based experiments to understand the role of charge dynamics in these systems. Assuming that SET operates as an efficient charge detection system we can expect to understand the underlying physics of charge transport and charge fluctuations in these materials for a range of doping. Experiments such as these can be classed in a general sense as mesoscopic and nano characterization of cuprates and related materials. In principle such experiments can show if electron is fractionalized in cuprates as indicated by ARPES data. In contrast to flux trapping experiments SET based experiments are more direct in providing evidence about spin-charge separation. In addition a detailed picture of nano charge dynamics in cuprates may be obtained.

I. INTRODUCTION

Keeping the properties of the cuprates and related materials in mind [see below], in this short note we further discuss our original suggestion to the possibility of Single Electron Tunneling Transistor [SET] based experiments which can probe the charge dynamics in HTSC cuprates [1], in particular the detection of charge-rich and charge-poor [i.e. stripes] and the important question of detection of fractional charge $q_f e$ carried by Luttinger excitation [*The Luttinger excitation is fractionalized and the elementary excitation carries the fractional charge $q_f e$ instead of the quantum of charge e of the electron*]. The HTSC materials are doped Mott insulators, in other words the parent compounds of HTSC material are unusual insulators. Superconductivity occurs when they are appropriately doped away from stoichiometry.

A. Motivation

We now outline the theoretical rationale behind our current proposal, in order to aid in the understanding and reasons pertaining to our suggestion. In a previous work one of us [2] has advanced the conjecture that one should attempt to model the phenomena of antiferromagnetism and superconductivity by using quantum symmetry group. Following this conjecture to model the phenomena of antiferromagnetism and superconductivity by quantum symmetry groups, three toy models were proposed [3], namely, one based on $SO_q(3)$ the other two constructed with the $SO_q(4)$ and $SO_q(5)$ quantum groups. Possible motivations and rationale for these choices were outlined [3]. In [4] a model to describe quantum liquids in transition from 1d to 2d dimensional crossover using quantum groups was outlined. In [6] the classical group $SO(7)$ was proposed as a toy model to understand the connections between the competing phases and the phenomenon of pseudo-gap in High Temperature Superconducting Materials [HTSC]. Then we proposed in [7] an idea to construct a theory based on patching critical points so as to simulate the behavior of systems such as cuprates. To illustrate our idea we considered an example discussed by Frahm et al., [5]. The model deals with antiferromagnetic spin-1 chain doped with spin-1/2 carriers. In [8] the connection between Quantum Groups and 1-dimensional [1-d] structures such as stripes was outlined. The main point of [8] is to emphasize that *1-d structures play an important role in determining the physical behaviour [such as the phases and types of phases these materials are capable of exhibiting] of cuprates and related materials*. In order to validate our quantum group conjecture for the cuprates, we have considered the connection between quantum groups and strings [9,10]. Indeed the 1-d structure can be regarded as one of the basic building blocks of a new formulation of correlated condensed matter physics. In fact we propose this as a definition of what we mean by a strongly correlated system. Already known example is when Landau quasiparticles give away to Luttinger liquid in 1-d. A possible definition of [strongly] correlated electron system is as follows: We define a [strongly] correlated electron

system as one where electron-electron interactions are *string-like*: Examples: BCS, and Stripes.

B. Some properties of cuprates

The cuprates seem to exhibit statistics, dimensionality and phase transitions in novel ways. We summarize the following interesting features that appear to arise in these materials, and motivates us to suggest SET based experiments to understand charge dynamics in these materials:

- Charge-spin separation:-Indications for electron fractionalization from Angle-Resolved Photoemission Spectroscopy [ARPES] have been reported [12]. We note that the Fermi liquid is characterized by sharp fermionic quasiparticle excitations and has a discontinuity in the electron momentum distribution function. In contrast the Luttinger liquid is characterized by charge e spin 0 bosons and spin 1/2 charge 0 and the fermion is a composite of these [i.e. fractionalization]. It is well-known that transport properties are defined via correlation functions. The correlation functions of a Luttinger liquid have a power law decays with exponents that depend on the interaction parameters, see below, section II. Consequently the transport properties of a Luttinger liquid are very different from that of a Fermi liquid. Photoemission experiments on Mott insulating oxides seems to indicate the spinon and holon excitations of a charge Luttinger liquid. However the experimental signatures of Luttinger liquid are not totally convincing. To this end we propose SET based experiments to determine the Luttinger liquid behaviour of the cuprates, see below.
- d-wave symmetry:-Experimental evidence for predominantly d-wave pairing symmetry in both hole- and electron-doped high T_c cuprate superconductors has been reported by C.C. Tsuei and J.R. Kirtley [13].
- Stripes:-For recent overview see abstracts of Stripes 2000 conference. In our way of thinking stripes arise out of strongly correlated 1-d systems which are charge transfer insulators, a specific case of Mott Insulators. Thus as AF Mott Insulating state is doped, see Fig. 1 it undergoes transition to a strange metal[SM], to normal metal [NM] and superconducting state [SC]. We note that the bandgap in the Mott Insulating state is on the order of 2 eV, and SC Δ is on the order of meV.
- 1/8 problem:-The recent experimental work of Koike et al. [14] indicates that the dynamical stripe correlations of holes and spins exist in Bi-2212, Y-123 and also La-124 and that they tend to be pinned by a small amount of Zn at $p \sim 1/8^*$, leading to

*where p is the hole concentration per Cu

1/8 anomaly.

- **Pseudogap:**—We can consider the reduction of the density of states near the Fermi energy as a pseudogap. For example Nakano et al. [11], claim that magnetic susceptibility measurements of the cuprate $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ [LSCO] in the T-x phase diagram show two crossover lines $T_{max}(x)$ and $T^*(x)$ [where $T_c < T^* < T_{max}$], see Fig. 1. Thus these lines $T_{max}(x)$ and $T^*(x)$ are naturally termed the high and low energy pseudogap respectively. These lines in the T- $x^\dagger$ diagram are both monotonically decreasing with rising hole concentration x . Below T_{max} magnetic susceptibility exhibits a broad peak which in the usual interpretation is taken to arise from the gradual development of the antiferromagnetic spin correlation. The lower crossover line T^* is taken to represent the temperature below which a spin gap opens up in the magnetic excitation spectrum around $q = (\pi, \pi)$.
- **Carrier Inhomogeneity:** We have previously emphasized the carrier [electron] inhomogeneity in our modelling of HTSC materials [3] material. In contrast many models of HTSC assume that charge carrier introduced by doping distribute uniformly, leading to an electronically homogeneous system, as in normal metals. However recent experimental work [15] confirms our intuition, which is encouraging. This inhomogeneity is expected to be manifested in both the local density of states spectrum and superconducting gap.

C. Luttinger Liquid

For the benefit of the non-theoretical reader we now summarize and state some relevant definitions, formulas and properties of Luttinger Liquid [LL], for more details see [16,17]. Moreover, since Single-Walled Nanotube [SWNT] is involved in our suggested configurations, see section II, we give some relevant details of SWNT.

- Experimentally, one place where LL behavior has been reported, is in the context of carbon nanotubes by Bockrath et al., [18]. LL behavior arises out of strong electron correlations, thus if $g = (1 + 2U/\Delta)^{-1/2}$ measures the strength of interactions between electrons, where U is the charging energy of the nanotube and Δ is the energy-level spacing. Very simply the LL is *one-dimensional* correlated electron state, parameterized by coupling g . $g = 1$ gives the case of non-interacting electrons and $g \ll 1$ represents strong repulsive interactions.
- The transport properties of LL are dramatically different, for example, from a Fermi Liquid [FL]. In a FL tunnelling amplitude of an electron is energy independent, in

$^\dagger x$ is same as δ

contrast in a clean LL we expect that tunnelling amplitude is expected to show a power law behavior. This implies that conductance G of LL at small biases [i.e. $eV \ll k_B$] is dictated by

$$G(T) \propto T^\alpha \quad (1)$$

for large biases [i.e. $eV \gg k_B$] the differential conductance is given by

$$\frac{dI}{dV} \propto V^\alpha. \quad (2)$$

Clearly the crucial parameter is α , which depends on the number of the one-dimensional channels, and on where the electron tunnels to, the bulk or the end of the LL. Thus for a single-walled nanotube [SWNT], with four conducting modes at the Fermi energy E_F

$$\begin{aligned} \alpha_{bulk} &= (g + g^{-1} - 2)/8, \\ \alpha_{end} &= (g^{-1} - 1)/4. \end{aligned} \quad (3)$$

Clearly if $g = 1$ we obtain the non-interacting case with α vanishing.

II. SUGGESTED CONFIGURATIONS

A. SET

- Definition: In the most basic form the definition of SET reads [19]: SET transistor is a small conductor [typically a metallic island] placed between two bulk electrodes, that forms two tunnel junctions with these electrodes.
- SET as Quantum detectors SET is a natural measuring device for *charge states* mesoscopic Josephson junctions [JJ]: One application is in potential quantum logic circuits. We suggest: To measure Charge fractionalization [CF] in cuprates and other charge nanodynamics in HTSC and related materials.

To realize this we suggest three possible configurations below. Encouraging is the claim by Averin that in the advantage of co-tunneling for quantum signal detection is a *weaker* back-action noise on the measured system produced by the SET transistor.

- SET/FET: A room temperature! SET has been demonstrated by Mutsomoto [20]. Coulomb oscillations are seen from which the gate capacitance is determined to be 8×10^{-20} F. Since we are mainly interested in the action of the SET device at lower temperatures the width of the gate insulator for sidegate SET can be much lower than 964 nm, which is needed at room temperature to prevent gate leakage current, for example, it can be on the order of 300 nm.

B. Configurations

- SET-JJ:SET coupled to HTSC Josephson junction:-The SET works on Coulomb energy and on the process of tunneling. The Coulomb charging of the island takes place due to electron tunneling. The current I in this system depends on the electrostatic potential of the island which in turn is controlled by external gate voltage V_g . The SET transistor operation as a detector entails the measurement of the variations of the voltage V_g which is sensitive to the current I . It is natural to consider the SET as a quantum detector [19] since the SET transistor is the natural measuring device for the potential quantum logic circuits based on the charge states of mesoscopic Josephson junctions [19]. Moreover it is natural to consider the SET as a quantum detector if one carefully consider its noise properties [19], since it appears that in the co-tunneling region, for quantum signal detection a *weaker* back-action noise is produced by the SET transistor on the measured system. We propose to couple the SET transistor to HTSC Josephson junction and study the charge dynamics of the HTSC materials for various levels of doping. The ‘insulating’ layer in the Josephson junction is chosen for a particular value of doping. For example, in LSCO system it is known that that superconductivity is suppressed to some extent at hole concentration per Cu of 1/8. This is considered to be due to existence of stripes. One would expect measurable change in SET current as one goes from this region towards the ‘purely’ AF-phase Region I] and ‘purely’ superconducting, Fig. 1. In principle we can explore all the underdoped region of T- δ phase diagram, Fig. 1 by using different values of doping.

It is thought that in AF [Region I, Fig. 1] diagonal stripes develop, whereas in Region II one has vertical stripes, which allow charge transport. It would be possible with this configuration to see the evolution of diagonal to vertical stripes, as doping is varied and one crosses from the AF to the SM and SG region.

- SET-SWNT-JJ: This is a slightly more complicated version of the previous case. The same remarks apply here. One of the advantages of this scheme is that we are coupling two LL, see Fig. 2. Upto our knowledge this is the first circuit with LL wires. However, practical problems can arise due to the ‘contacts’ which could destroy the power law dependence a characteristic of LL. However, it has been recently shown by S. Hügler [21] in the study of electron tunneling from a tip or a lead into an interacting quantum wire described by LL that the dynamic image potential is not strong enough to alter the power-law exponents entering the tunneling density of states.
- SET transistor coupled to ‘HTSC material’ SET transistor:- In this set-up we propose to couple a SET transistor to a ‘HTSC material’ SET transistor. In the simplest case the ‘metallic’ island in ordinary SET is replaced with ‘HTSC material’ for a value of doping which is in the region of T- δ phase diagram which corresponds to metallic phase and ‘strange’ metallic [SM] phase. The SM phase is ascribed to coexistence of superconductivity and stripe phases. In this region the material, if it were perfectly

oriented would be a superconductor in one direction and a strongly-correlated insulator in the other. Thus one can quantify the SM and metallic phases of HTSC materials in detail by using charge transport properties measured with SET.

It is known that in the superconducting tunnel junctions coherent tunneling of Cooper pairs competes with the Coulomb blockade [22]. Thus one must consider how the shot noise could be affected due to quasiparticle scattering and coherence of the supercurrent. Choi et al. [23] have considered the shot noise in superconducting SET near a resonance Cooper pair tunneling. The set-up is typical, as shown in Fig. 3, where two small tunnel junctions are in series, with a small central electrode. This system couples capacitively to a gate electrode and via tunneling to the two leads, Fig. 3. One intuitively expects that the shot noise [zero-frequency] must be suppressed if there is coherent oscillation of the Cooper pairs in the presence of Coulomb blockade. This is indeed found to be the case [23]. Keeping this in mind we can compare the coherent oscillation of the Cooper pairs in the SM and full superconducting state. In the SM case where the superconducting coexists with stripe phase the coherent oscillation would have a weaker effect on the shot noise compared to the case where HTSC superconducting state exists. In this manner by using the dependence of shot noise on coherent Cooper pair tunneling we can understand qualitatively and quantitatively the similarities of superconductivity in SM phase and in the ‘full’ superconducting phase.

- SET-Single-Cooper pair box:- Tsai et al. [24], have recently demonstrated the time and energy domain response of an artificially constructed two-level system, which is expected to form one of the possibilities for the basic bit of quantum computing [Qubit]. This device which has submicron size allows one to observe quantum coherent oscillations in a solid state system whose quantum states involve a macroscopic number of quantum particles. As already mentioned it has already been noted [19] that the SET is a natural measuring device for the potential quantum logic circuits based on the charge states of mesoscopic Josephson junctions, such as Single-Cooper pair box of Tsai et al. [24]. Keeping in mind that HTSC materials are *doped* Mott insulators [unlike the low-temperature superconductors], and consequently their superconductivity depends on the level of doping as is clear from the T - δ phase diagram, Fig. 1, so that one has underdoped, optimally doped and overdoped regions. It is interesting to think of an experiment that can give us a detailed look at the effect of changing T_c [as doping is varied] on the charge transport. A possible experimental set-up for this measurement could consist of SET transistor coupled to a HTSC single-Cooper pair box. In this configuration the SET is in essence coupled to a two-level system. An equivalent circuit of Cooper-pair box is shown in Fig. 4, with the condition $J_L = E_J$, $J_R = 0$, and one of the lead has to be used as a probe gate [i.e. $V_i = 2\Delta/e$] the other is set to zero [i.e. $V_i = 0$], $i = L, R$. Here J_i is the Josephson coupling energy. In this suggested set-up we can in principle monitor the charge dynamics in the whole range of doping when the material is in the SC state, i.e. Region III, in Fig. 1. We can study

by such an experiment if there is a change in charge transport as we vary the doping but remain within region III, in Fig. 1.

Thus given the above set-ups we can in principle explore the charge dynamics in every region of the rich phase diagram of HTSC materials Fig. 1. Distinctions must be made between superconducting, normal and strange metallic SETs. As is clear from our various set-ups we will not only encounter superconducting, normal and SM SETs but also hybrids as we probe different regions of HTSC phase diagram by varying the doping. Yet another challenging problem is to study magnetotransport of charged stripes in HTSC materials in our SET based configurations described above. To characterize the transport properties in striped phase in above materials, the experiments must be calibrated against some standard, which clearly shows the one-dimensional transport behaviour and also must be closely related to the cuprate superconductors. One such material is $\text{La}_{1.4-x}\text{Nd}_{0.6}\text{Sr}_x\text{CuO}_4$ ($x=0.1, 0.12, 0.15$) which is stripe-ordered non-superconducting relative of HTSC cuprates. Another standard could be the heavily underdoped YBCO system, where charged stripes can be detected in the magnetoresistance [25].

III. CONCLUSIONS

In conclusion we have proposed that SET based experiments can detect charge fractionalization in cuprates and related materials. To this end we have proposed several experimental configurations which can achieve this goal. However our suggestion is not limited to charge fractionalization since SET based experiments can be used to characterize and understand the underlying physics of charge transport and charge fluctuations in these and related materials for a range of doping. Experiments such as these can be classed in a general sense as mesoscopic and nano characterization of cuprates and related materials. One of the main point of our proposal can be summarized thus: If we follow the tunneling of an electron, we will ‘partially’ loose the electron as it encounters a strongly correlated electron state and our SET will register a fraction of an electron.

ACKNOWLEDGMENTS

The Sher Alam’s work is supported by the Japan Society for Technology [JST].

REFERENCES

- [1] Sher Alam et al., *SET based experiments for HTSC materials* cond-mat/0011037.
- [2] Sher Alam, *A Conjecture for possible theory for the description of high temperature superconductivity and antiferromagnetism*. Proceedings of Quantum Phenomena in Advanced Materials at High Magnetic Fields, 4th International Symposium on Advanced Physical Fields [APF-4]. KEK-TH-607, KEK Preprint 98-xxx, cond-mat/9812060.
- [3] Sher Alam, *Quantum Group based Modelling for the description of high temperature superconductivity and antiferromagnetism*, Phys. Lett. A272, (2000), 107-112. KEK-TH-613, KEK Preprint 98-xxx, cond-mat/9903038, cond-mat/0102456.
- [4] Sher Alam et al., *Theoretical modeling for quantum liquids from 1d to 2d dimensional crossover using quantum groups*. KEK-TH-619. KEK Preprint 99-xxx, cond-mat/990345.
- [5] Holger. Frahm et al., Phys. Rev. Lett. **81**, (1998), 2116.
- [6] Sher Alam et al., *The Choice of symmetry group for cuprates*, cond-mat/0004269.
- [7] Sher Alam et al., *The patching of critical points using quantum groups*, cond-mat/0004350.
- [8] Sher Alam, *Quantum group conjecture and Stripes* cond-mat/0005168.
- [9] Sher Alam et al., *Quantum group, Strings, and HTSC materials*, cond-mat/0102097.
- [10] M. Kaku, *Strings, Conformal Fields, and Topology: An Introduction*, Springer-Verlag, 1991.
- [11] T. Nakano et al., J. Phys. Soc. Jpn. **67**, (1998), 2622.
- [12] D. Orgad et al., cond-mat/0005457.
- [13] C.C. Tsuei, J.R. Kirtley, *d-wave pairing symmetry in cuprate superconductors*, cond-mat/0004185.
- [14] Y. Koike et al., Stripes 2000 and 13th International Symposium on Superconductivity [ISS 2000].
- [15] S.H.Pan et al., *Discovery of microscopic electronic inhomogeneity in the high- T_c superconductor $Bi_2Sr_2CaCu_2O_{8+x}$* cond-mat/0107347.
- [16] Johannes Voit, *One-dimensional Fermi liquids* cond-mat/9510014. Updates are included in cond-mat/9510014 relative to the older version in Repts. Prog. Phys. **57** (1994) 977-1116.
- [17] Johannes Voit, *A brief introduction to Luttinger liquids* cond-mat/0005114.
- [18] Marc Bockrath et al., Nature **397** (1999) 598-601.
- [19] For example see, D.V. Averin, cond-mat/0010052.
- [20] Kazuhiko Matsumoto, Int. J. of High Speed Electronics and systems **10**(2000)83-91.
- [21] S. Hügler et al., cond-mat/0004305, April 2000.
- [22] T. A. Fulton et al., Phys. Rev. Lett. **63**, (1989), 1307. A. Maassen van den Brink et al., Phys. Rev. Lett. **67**, (1991), 21
- [23] Mahn-Soo Choi et al., cond-mat/0102341, Feb. 2001
- [24] J. S. Tsai et al., 13th International Symposium on Superconductivity [ISS 2000] and references therein.

[25] A. N. Lavrov et al., cond-mat/9910316; Phys. Rev. Lett. **83**, (1999), 2813-2816.

FIGURES

FIG. 1. HTSC phase diagram, showing the varied phases exhibited in temperature $[T]$ - doping δ plane. The psuedogap curve $T_{\max}^*$ is from tunneling data, and T^* is from NMR and specific heat experiments

FIG. 2. SET, SWNT, and SIS configuration to measure CF

FIG. 3. Schematic diagram of Superconducting SET

FIG. 4. Equivalent circuit of Cooper-pair box




Fig. 1: HTSC phase diagram, showing the varied phases exhibited in temperature $[T]$ -doping δ plane. The pseudogap curve T_{max}^* is from tunneling data, and T^* is from NMR and specific heat experiments.




Fig. 2: SET, SWNT, and SIS configuration to measure CF.




Fig. 3: Schematic diagram of Superconducting SET.




Fig. 4: Equivalent circuit of Cooper-pair box.